

AFRICAN GREEN

Material: Granite

Origin: South Africa

Apparent density (Kg/m3) -----	2890
Open porosity - EN1936 -----	0,40%
Abrasion resistance (mm) - EN14157-----	17
Water absorption at atmospheric pressure - EN13755 -----	0,12%
Resistance to bending stress (MPA) - EN12372 -----	12
Anchor breaking load (N) - EN13364 -----	3900
Thermal shock (change in mass) - EN14066 -----	does not change
Compressive resistance (MPA) - EN1926 -----	190
Frost resistance (48 cycles) (reduction in bending resistance) - EN12371 -----	2,9

TIERA Stones Sp. z o.o. Sp.k.

Business Link - Maraton - Krolowej Jadwigi 43 - Poznan 61-871 - Poland - T+48 606 461 061 - info@tierastones.com